

**Number of Lots According to Physical Fiber properties**  
**From Beginning of September 2010 To The End of December 2010**  
**Giza 80**

Length (mm)

Classes	28.0-	29.0-	30.0-	31.0-	32.0&more	Total	Average	Range
NoofLots	15	106	81	11	1	214	29.9	28.5-32.5
(%)	7.01	49.53	37.85	5.14	0.47			

Uniformity %

Classes	81.0-	83.0-	85.0&more	Total	Average	Range
NoofLots	81	114	19	214	83.4	82.0-86.0
(%)	37.85	53.27	8.88			

Strength (gm/Tex )

Classes	33.0-	35.0-	37.0-	39.0&more	Total	Average	Range
NoofLots	66	96	35	17	214	35.9	34.0-40.0
(%)	30.84	44.86	16.36	7.94			

Micronaire (U/finch )

Classes	3.6-	3.8-	4.0-	4.2-	4.4-	4.6&more	Total	Average	Range
NoofLots	8	49	78	56	22	1	214	4.1	3.7-4.7
(%)	3.74	22.9	36.45	26.17	10.28	0.47			

\* No. of Bales maximum 30 for each Lot

\* Avg.Weigh of Bale 325 kg .

**Number of Lots According to Physical Fiber properties**  
**From Beginning of September 2010 To The End of December 2010**  
**Giza 86**

Length (mm)

Classes	30.0-	31.0-	32.0-	33.0-	34.0&more	Total	Average	Range
NoofLots	22	2828	1749	206	2	4807	31.9	30.5-34.5
(%)	0.46	58.83	36.38	4.29	0.04			

Uniformity %

Classes	83.0-	85.0-	87.0-	89.0&more	Total	Average	Range
NoofLots	598	2824	1238	147	4807	86.3	84.0-90.0
(%)	12.44	58.75	25.75	3.06			

Strength (gm/Tex )

Classes	40.0-	42.0-	44.0-	46.0-	48.0&more	Total	Average	Range
NoofLots	1122	1957	1367	357	4	4807	43.4	41.0-49.0
(%)	23.34	40.71	28.44	7.43	0.08			

Micronaire (U/finch )

Classes	3.0-	3.2-	3.4-	3.6-	3.8-	4.0-	4.2-	4.4-	4.6-	4.8&more	Total	Average	Range
NoofLots	3	19	26	107	555	1549	1458	777	276	37	4807	4.2	3.1-4.9
(%)	0.06	0.4	0.54	2.23	11.55	32.22	30.33	16.16	5.74	0.77			

\* No. of Bales maximum 30 for each Lot

\* Avg.Weigh of Bale 325 kg .

**Number of Lots According to Physical Fiber properties**  
**From Beginning of September 2010 To The End of December 2010**

**Giza 87**

Length (mm)

Classes	34.0&more	Total	Average	Range
NoofLots	2	2	34.3	34.5-34.5
(%)	100			

Uniformity %

Classes	84.0&more	Total	Average	Range
NoofLots	2	2	85.2	85.0-85.0
(%)	100			

Strength (gm/Tex )

Classes	41.0&more	Total	Average	Range
NoofLots	2	2	41.7	42.0-42.0
(%)	100			

Micronaire (U/finch )

Classes	3.0&more	Total	Average	Range
NoofLots	2	2	3.1	3.1-3.1
(%)	100			

\* No. of Bales maximum 30 for each Lot

\* Avg.Weigh of Bale 325 kg .

**Number of Lots According to Physical Fiber properties**  
**From Beginning of September 2010 To The End of December 2010**

**Giza 88**

Length (mm)

Classes	34.0-	35.0-	36.0&more	Total	Average	Range
NoofLots	364	611	151	1126	35.3	34.5-36.5
(%)	32.33	54.26	13.41			

Uniformity %

Classes	84.0-	86.0-	88.0-	90.0&more	Total	Average	Range
NoofLots	148	655	318	5	1126	87.3	85.0-91.0
(%)	13.14	58.17	28.24	0.44			

Strength (gm/Tex )

Classes	41.0-	43.0-	45.0-	47.0-	49.0&more	Total	Average	Range
NoofLots	68	302	416	310	30	1126	45.8	42.0-50.0
(%)	6.04	26.82	36.94	27.53	2.66			

Micronaire (U/inch )

Classes	3.0-	3.2-	3.4-	3.6-	3.8-	4.0-	4.2-	4.4&more	Total	Average	Range
NoofLots	3	6	43	287	419	266	100	2	1126	3.9	3.1-4.5
(%)	0.27	0.53	3.82	25.49	37.21	23.62	8.88	0.18			

\* No. of Bales maximum 30 for each Lot

\* Avg.Weigh of Bale 325 kg .

## Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of December 2010

### Giza 90

Length (mm)

Classes	27.0-	28.0-	29.0-	30.0&more	Total	Average	Range
NoofLots	244	292	84	5	625	28.2	27.5-30.5
(%)	39.04	46.72	13.44	0.8			

Uniformity %

Classes	78.0-	80.0-	82.0-	84.0-	86.0&more	Total	Average	Range
NoofLots	1	163	336	118	7	625	82.8	79.0-87.0
(%)	0.16	26.08	53.76	18.88	1.12			

Strength (gm/Tex )

Classes	29.0-	31.0-	33.0-	35.0-	37.0&more	Total	Average	Range
NoofLots	23	203	290	96	13	625	33.6	30.0-38.0
(%)	3.68	32.48	46.4	15.36	2.08			

Micronaire (U/finch )

Classes	3.0-	3.2-	3.4-	3.6-	3.8-	4.0-	4.2-	4.4&more	Total	Average	Range
NoofLots	5	15	33	53	105	174	183	57	625	4.1	3.1-4.5
(%)	0.8	2.4	5.28	8.48	16.8	27.84	29.28	9.12			

\* No. of Bales maximum 30 for each Lot

\* Avg.Weigh of Bale 325 kg .

## Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of December 2010

### Giza 92

Length (mm)

Classes	34.0&more	Total	Average	Range
NoofLots	1	1	34.3	34.5-34.5
(%)	100			

Uniformity %

Classes	87.0&more	Total	Average	Range
NoofLots	1	1	87.4	88.0-88.0
(%)	100			

Strength (gm/Tex )

Classes	43.0&more	Total	Average	Range
NoofLots	1	1	43.8	44.0-44.0
(%)	100			

Micronaire (U/finch )

Classes	3.2&more	Total	Average	Range
NoofLots	1	1	3.2	3.3-3.3
(%)	100			

\* No. of Bales maximum 30 for each Lot

\* Avg.Weigh of Bale 325 kg .