

Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of June 2011

Giza 70

Length (mm)

Classes	33.0-	34.0-	35.0&more	Total	Average
NoofLots	10	6	4	20	34.2
(%)	50	30	20		

Uniformity %

Classes	85.0-	87.0&more	Total	Average
NoofLots	8	12	20	86.9
(%)	40	60		

Strength (gm/Tex)

Classes	41.0-	43.0-	45.0&more	Total	Average
NoofLots	7	10	3	20	43.3
(%)	35	50	15		

Micronaire (U/inch)

Classes	3.0-	3.2-	3.4-	3.6-	3.8-	4.0-	4.2&more	Total	Average
NoofLots	1	2	2	1	9	3	2	20	3.8
(%)	5	10	10	5	45	15	10		

* No. of Bales maximum 30 for each Lot

* Avg.Weigh of Bale 325 kg .

Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of June 2011

Giza 80

Length (mm)

Classes	28.0-	29.0-	30.0-	31.0-	32.0&more	Total	Average
NoofLots	49	175	108	16	1	349	29.8
(%)	14.04	50.14	30.95	4.58	0.29		

Uniformity %

Classes	80.0-	82.0-	84.0-	86.0&more	Total	Average
NoofLots	39	198	107	5	349	83.4
(%)	11.17	56.73	30.66	1.43		

Strength (gm/Tex)

Classes	30.0-	32.0-	34.0-	36.0-	38.0-	40.0&more	Total	Average
NoofLots	1	41	149	115	41	2	349	35.8
(%)	0.29	11.75	42.69	32.95	11.75	0.57		

Micronaire (U/inch)

Classes	3.0-	3.2-	3.4-	3.6-	3.8-	4.0-	4.2-	4.4-	4.6&more	Total	Average
NoofLots	1	1	1	15	81	130	84	34	2	349	4.1
(%)	0.29	0.29	0.29	4.3	23.21	37.25	24.07	9.74	0.57		

* No. of Bales maximum 30 for each Lot

* Avg.Weigh of Bale 325 kg .

Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of June 2011

Giza 86

Length (mm)

Classes	30.0-	31.0-	32.0-	33.0-	34.0&more	Total	Average
NoofLots	25	7079	4743	584	2	12433	31.9
(%)	0.2	56.94	38.15	4.7	0.02		

Uniformity %

Classes	82.0-	84.0-	86.0-	88.0&more	Total	Average
NoofLots	15	5737	5688	993	12433	86.2
(%)	0.12	46.14	45.75	7.99		

Strength (gm/Tex)

Classes	39.0-	41.0-	43.0-	45.0-	47.0&more	Total	Average
NoofLots	1106	5175	4254	1733	165	12433	43.1
(%)	8.9	41.62	34.22	13.94	1.33		

Micronaire (U/inch)

Classes	3.0-	3.2-	3.4-	3.6-	3.8-	4.0-	4.2-	4.4-	4.6-	4.8&more	Total	Average
NoofLots	10	51	86	279	1657	3740	3672	2136	707	95	12433	4.2
(%)	0.08	0.41	0.69	2.24	13.33	30.08	29.53	17.18	5.69	0.76		

* No. of Bales maximum 30 for each Lot

* Avg.Weigh of Bale 325 kg .

Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of June 2011

Giza 87

Length (mm)

Classes	34.0&more	Total	Average
NoofLots	3	3	34.3
(%)	100		

Uniformity %

Classes	84.0&more	Total	Average
NoofLots	3	3	85.4
(%)	100		

Strength (gm/Tex)

Classes	41.0&more	Total	Average
NoofLots	3	3	41.7
(%)	100		

Micronaire (U/inch)

Classes	3.0-	3.2&more	Total	Average
NoofLots	2	1	3	3.2
(%)	66.67	33.33		

* No. of Bales maximum 30 for each Lot

* Avg.Weigh of Bale 325 kg .

Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of June 2011

Giza 88

Length (mm)

Classes	34.0-	35.0-	36.0&more	Total	Average
NoofLots	1365	2203	465	4033	35.3
(%)	33.85	54.62	11.53		

Uniformity %

Classes	84.0-	86.0-	88.0-	90.0&more	Total	Average
NoofLots	632	2473	909	19	4033	87.1
(%)	15.67	61.32	22.54	0.47		

Strength (gm/Tex)

Classes	40.0-	42.0-	44.0-	46.0-	48.0&more	Total	Average
NoofLots	44	1041	1633	1053	262	4033	45.1
(%)	1.09	25.81	40.49	26.11	6.5		

Micronaire (U/inch)

Classes	2.8-	3.0-	3.2-	3.4-	3.6-	3.8-	4.0-	4.2-	4.4&more	Total	Average
NoofLots	1	13	33	358	1189	1472	752	201	14	4033	3.9
(%)	0.02	0.32	0.82	8.88	29.48	36.5	18.65	4.98	0.35		

* No. of Bales maximum 30 for each Lot

* Avg.Weigh of Bale 325 kg .

Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of June 2011

Giza 90

Length (mm)

Classes	26.0-	27.0-	28.0-	29.0-	30.0&more	Total	Average
NoofLots	2	330	405	111	6	854	28.2
(%)	0.23	38.64	47.42	13	0.7		

Uniformity %

Classes	78.0-	80.0-	82.0-	84.0-	86.0&more	Total	Average
NoofLots	4	224	466	149	11	854	82.8
(%)	0.47	26.23	54.57	17.45	1.29		

Strength (gm/Tex)

Classes	26.0-	28.0-	30.0-	32.0-	34.0-	36.0-	38.0&more	Total	Average
NoofLots	2	6	142	377	266	57	4	854	33.5
(%)	0.23	0.7	16.63	44.15	31.15	6.67	0.47		

Micronaire (U/inch)

Classes	2.8-	3.0-	3.2-	3.4-	3.6-	3.8-	4.0-	4.2-	4.4-	4.6&more	Total	Average
NoofLots	1	5	19	46	77	130	226	248	101	1	854	4.1
(%)	0.12	0.59	2.22	5.39	9.02	15.22	26.46	29.04	11.83	0.12		

* No. of Bales maximum 30 for each Lot

* Avg.Weigh of Bale 325 kg .

Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of June 2011

Giza 92

Length (mm)

Classes	31.0-	32.0-	33.0-	34.0&more	Total	Average
NoofLots	1	6	11	1	19	33.1
(%)	5.26	31.58	57.89	5.26		

Uniformity %

Classes	84.0-	86.0-	88.0&more	Total	Average
NoofLots	5	12	2	19	86.7
(%)	26.32	63.16	10.53		

Strength (gm/Tex)

Classes	40.0-	42.0-	44.0-	46.0&more	Total	Average
NoofLots	1	6	6	6	19	44.7
(%)	5.26	31.58	31.58	31.58		

Micronaire (U/inch)

Classes	2.6-	2.8-	3.0-	3.2-	3.4-	3.6&more	Total	Average
NoofLots	1	1	3	1	11	2	19	3.4
(%)	5.26	5.26	15.79	5.26	57.89	10.53		

* No. of Bales maximum 30 for each Lot

* Avg.Weigh of Bale 325 kg .

Number of Lots According to Physical Fiber properties

From Beginning of September 2010 To The End of June 2011

Length (mm)

Classes	31.0&more	Total	Average
NoofLots	1	1	31.8
(%)	100		

Uniformity %

Classes	87.0&more	Total	Average
NoofLots	1	1	87.5
(%)	100		

Strength (gm/Tex)

Classes	44.0&more	Total	Average
NoofLots	1	1	44.5
(%)	100		

Micronaire (U/inch)

Classes	4.2&more	Total	Average
NoofLots	1	1	4.3
(%)	100		

* No. of Bales maximum 30 for each Lot

* Avg.Weigh of Bale 325 kg .