

## **Physical Fiber Properties for Short Fiber Cotton Varieties**

## Measured By HVI & Micromat

## Cotton Arbitration & Testing General Organization From 1/9/2022 Until 19/12/ 2022 season 2021/2022

**General Administration for Information Systems & Digitization** 

property	variety	LIMA COTTON	EDESSA COTTON
Mic Reading	u/inch	4.71	4.71
Upper Half Mean Length	(mm)	29,51	28.27
Uniformity Index	(%)	83,6	84.0
Short fiber	(%)	7,0	7.2
Strength	(gm/tex)	30.2	30.1
Reflectance	Rd	72,1	65.5
Yellowness	+b	8,0	8.5
SCI		133	128
Maturity	(%)		
Hair Weight	(m.tex)		
Trash	%	14.9	22.0
Neps Count/gram		75	110
No. of samples		11	19

Chairman Eng. | Mohamed Khedr